

Technical Data Sheet of Chloroprene Rubber 114

Chemical Name: Chloroprene Rubber 114

CAS NO.: 9010-98-4

Technical Data of DCR114:

Items	Specifications	
Mooney Viscosity (ML 100°C₁₊₄)	DCR 1141	DCR 1142
	30-45	46-60
Mooney Scorch (MSt₅, min)	25	
Tensile Strength, ≥Mpa	20	
Modulus at 500%, Mpa	2-5	
Elongation at break, ≥%	800	
Volatile matter, ≤%	1.5	
Ash content, ≤%	1.5	
Appearance	Light brown chips	

Application:

For making transmission belts such as timing belts, ribbed belts, etc.

Package:

Packed in paper bags, 25kg net each.

Storage:

Keep under cover in a cool and well-ventilated place, avoiding direct sunlight.

The shelf life is one year below 20°C and half a year below 30°C from the date of production.