

Technical Date Sheet of Chloroprene Rubber SN-241

Chemical Name: 2-CHLORO-1,3-BUTADIENE POLYMERS

CAS NO.: 9010-98-4

Technical Data of Chloroprene Rubber SN-241:

Items	Index
Appearance	White or beige chips
Molecular Weight	100,000~600,000
Density	1.23
Softening Temperature (°C)	80
Tg(°C)	-38~-40
Specific Heat (KJ/kg•°C)	2.18
Volume Resistance (Ω•cm)	10 ⁹ ~ 10 ¹²
Crystallization Rate	Fast
Brookfield Solution Viscosity (mpa.s, 10% toluene solution at 25°C)	240-400
Volatiles(wt.%)	≤1.3
Ash(wt.%)	≤1.0

Application:

SN241, which is a basic raw material for preparing adhesive cements, can be used alone or combination with other types, especially, suitable for preparing spraying adhesive. Adhesive is suitable for bonding of the shoe industry, rubber leather, wood, metal and construction materials

Package:

Packed in 25kg kraft-plastic bag.

Storage:

Maintain storage in a cool and well-ventilated area, ensuring it is shielded from direct sunlight. It is advisable to keep the temperature below 25°C.