

Technical Date Sheet of Chloroprene Rubber SN-240T

Chemical Name: 2-CHLORO-1,3-BUTADIENE POLYMERS

CAS NO.: 9010-98-4

Technical Data of Chloroprene Rubber SN-240T:

Items	Index
Appearance	White or beige chips
Molecular Weight	100,000~600,000
Density	1.23
Softening Temperature (°C)	80
Tg(°C)	-38~-40
Specific Heat (KJ/kg•°C)	2.18
Volume Resistance (Ω•cm)	$10^9 \sim 10^{12}$
Crystallization Rate	Fast
Brookfield Solution Viscosity (mpa.s, 10% toluene solution at 25°C)	100-240
Volatiles(wt.%)	≤0.8
Ash(wt.%)	≤1.0

Application:

1. SN-240T serves as a fundamental precursor in the formulation of adhesive cements. It can be utilized either individually or in conjunction with various other raw materials, and is predominantly appropriate for the creation of low-viscosity spray adhesive formulations.
2. As an essential adhesive component, it is extensively employed in the footwear sector, as well as in the adhesion of rubber, leather, wood, metal, and construction materials.

Package:

Packed in 25kg kraft-plastic bag.

Storage:

Maintain storage in a cool and well-ventilated area, ensuring it is shielded from direct sunlight. It is advisable to keep the temperature below 25°C.