

Technical Data Sheet of Chloroprene Rubber SN-239

Chemical Name: 2-CHLORO-1,3-BUTADIENE POLYMERS

CAS NO.: 9010-98-4

Technical Data of Chloroprene Rubber SN-239:

Items	Index
Appearance	White or light grey chips
Molecular Weight	100,000~600,000
Density	1.23
Softening Temperature (°C)	80
Tg(°C)	-38~-40
Specific Heat (KJ/kg•°C)	2.18
Volume Resistance ($\Omega\cdot\text{cm}$)	$10^9 \sim 10^{12}$
Crystallization Rate	Medium
Mooney Viscosity ML(1+4) 100°C	110-130
Mooney Scorch MS t5 (min)	≥ 12
Module at 500% Elongation (MPa)	4-8
Tensile Strength (MPa)	≥ 13
Ultimate Elongation (%)	≥ 650
Volatiles(wt.%)	≤ 0.8
Ash(wt.%)	≤ 1.0

Application:

1. The primary use of SN-239 lies in its application within heavily filled compounds and in modifying the viscosity of adhesive formulations. Often, SN-239 is processed through extrusion as a hose, with notable utilization in the production of more rigid wire and cable sheaths.
2. SN-239 plays a role in the development of adhesives, particularly in the formulation of adhesive plasters.



江苏象化科技有限公司
JIANGSU ELEPHCHEM HOLDING LIMITED

Package:

Packed in 25kg kraft-plastic bag.

Storage:

Maintain storage in a cool and well-ventilated area, ensuring it is shielded from direct sunlight. It is advisable to keep the temperature below 25°C.